

AD-A265 379

ENTATION PAGE

Form Approved  
OMB No 0704-0188

2



estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering the collection of information, sending comments regarding this burden estimate or any other aspect of this burden to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204 Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188) Washington, DC 20503

1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE 2/27/93		3. REPORT TYPE AND DATES COVERED	
4. TITLE AND SUBTITLE Fracture Behavior of Ionomers and Ionomeric Blends				5. FUNDING NUMBERS  DAAL03-89-K-0044	
6. AUTHOR(S)  Masanori Hara					
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Rutgers University Department of Mechanics and Materials Science College of Engineering Piscataway, NJ 08855-0909				8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) U. S. Army Research Office P. O. Box 12211 Research Triangle Park, NC 27709-2211				10. SPONSORING/MONITORING AGENCY REPORT NUMBER  ARO 25424.15-ms	
11. SUPPLEMENTARY NOTES The view, opinions and/or findings contained in this report are those of the author(s) and should not be construed as an official Department of the Army position, policy, or decision, unless so designated by other documentation.					
12a. DISTRIBUTION/AVAILABILITY STATEMENT  Approved for public release; distribution unlimited				12b. DISTRIBUTION CODE  93-09482	
13. ABSTRACT (Maximum 200 words)  We have elucidated the deformation/fracture behavior of ionomers, and correlated them to their microstructure. We have also found important molecular variables to achieve enhanced fracture properties of ionomers: high ion content above a critical value, divalent counterions, and excess neutralizing agent. We have elucidated the structural changes associated with the change of each molecular variable. Subsequently, we have produced unique blends made of small amounts of ionomers and large amounts of unmodified polymers. They show synergistic mechanical behavior, retention of transparency of the unmodified polymer, good processability, and excellent cost performance. We have elucidated the structural characteristics responsible for these behavior.					
14. SUBJECT TERMS Deformation and Fracture Behavior, Ionomer Blends, Polystyrene Ionomer, PMMA Ionomer				15. NUMBER OF PAGES 2	
				16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT UNCLASSIFIED	18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED	19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED	20. LIMITATION OF ABSTRACT UL		

## FINAL REPORT

Title: Fracture Behavior of Ionomers and Ionomeric Blends

Grant Number: DAAL03-89-K-0044

### A Statement of the Problem Studied

The objective of this research is to elucidate the deformation and fracture behavior of ionomers and ionomer blends in the glassy state, to correlate them to their microstructure, and to exploit the possibility of using these materials as high-performance polymers.

### A Summary of the Most Important Results

Since technical materials were reported in semi-annual reports, only the most important results that we have obtained are briefly summarized here.

#### (1). Deformation/Fracture of Ionomers

We have found important molecular variables to achieve enhanced fracture properties (under both monotonic and dynamic loading conditions) of ionomers: these are (1) high ion content above a certain critical value (i.e., critical ion content, which depends on host polymers), (2) divalent counterions instead of monovalent ones, and (3) excess neutralizing agents. We have also elucidated the responsible structural changes for enhanced fracture properties as a result of changing molecular variable.

Specifically, we have found that the deformation mechanism of ionomers changes from crazing only to crazing plus shear deformation, either by increasing ion content or changing counterion from mono to divalent one. This is due to ionic crosslinking effect produced by ionic interactions, therefore, ionic crosslinkings can offer effective routes to modifying deformation behavior without losing processability, unlike the case of covalently crosslinked polymers.

We have proved that these are quite general findings applied to amorphous, glassy ionomers by investigating different type of ionomers: polystyrene(PS)-based ionomers (i.e., sulfonated polystyrene ionomer and styrene-co-methacrylate ionomer) and poly(methyl methacrylate)(PMMA)-based ionomers.

#### (2). Deformation/Fracture of Ionomer Blends

We have produced unique blends made of small amounts of ionomer and large amounts of unmodified polymers. This unique combination leads to the following advantageous properties: (1) synergistic mechanical behavior, (2) retention of transparency of the unmodified polymer, (3) excellent cost performance, and (4) good processability. We have elucidated the structural characteristics responsible for these behaviors. Again, the findings seem to be general, since we studied both PS-based blends and PMMA-based blends with basically similar results.

### A List of Participating Personnel

Prof. Masanori Hara  
Prof. John A. Sauer

Dr. Pean-Yue Jar  
Michelle Bellinger (earned Ph.D. during the period)  
Xiaolong Ma (earned Ph.D. during the period)  
Jeffrey Bodycomb

### A List of All Publications (Published)

Accession For	
NTIS	CRA&I
DTIC	TAB
Unannounced	
Justification	
By	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A-1	

"Deformation Behavior of Ionomers: Effect of Counterion and Plasticizer," Polym. Prepr., (Am. Chem. Soc., Div. Polym. Chem.), 30(2), 223 (1989)

"Effect of Molecular Variables on Crazing and Fatigue of Polymers," Adv. Polym. Sol., 91/92, 69-118 (1990)

"Fatigue Behavior of Ionomers: 2. Effect of Counterions on Sulfonated Polystyrene Ionomers," Macromolecules, 23, 4465-4469 (1990)

"Fatigue Behavior of Ionomers: 3. Effect of Excess Neutralizing Agent on Sulfonated Polystyrene Ionomers," Macromolecules, 23, 4964-4969 (1990)

"Deformation and Fracture of Ionomeric Blends: Sulfonated Polystyrene Ionomer/Polystyrene," Polym. Prepr., (Am. Chem. Soc., Div. Polym. Chem.), 31(1), 546 (1990)

"Effect of Sample History on Ionic Aggregate Structure of Sulfonated Polystyrene Ionomers," Polymer, 32, 1380-1383 (1991)

"Blends of Sulfonated Polystyrene and Polystyrene: Morphology and Deformation Modes," Polymer International, 26, 137-141 (1991)

"Deformation Modes and Morphology in PS/Sulphonated PS Ionomer Blends," Preprints, IUPAC International Symposium Polymer 91, p. 222 (1991)

"Dynamic Mechanical Properties of Sulfonated Polystyrene Ionomers," Polymer, 32, 1622-1626 (1991)

"Deformation/Fracture Behavior of Ionomer Blends," Proceedings of 8th International Conference on Deformation, Yield, and Fracture of Polymers, Paper No.35 (1991)

"Deformation and Fracture of Sulfonated Polystyrene Ionomer/Polystyrene Blends: Effect of Ion Content," Polym. Prepr., (Am. Chem. Soc., Div. Polym. Chem.), 32(3), 261 (1991)

"Deformation and Fracture Behavior of Polystyrene Ionomer and Ionomer Blends," Colloid Polymer Science, 270, 652-658 (1992)

"PMMA-based Ionomers. I. Dynamic Mechanical Properties," Polym Prepr., (Am. Chem. Soc., Div. Polym. Chem.), 33(1), 1214 (1992)